

1. A Chip Scale Package (CSP) comprising:

3 providing a silicon chip having I/O pads;

an under-ball metallurgy (UBM) layer on the surface of said

6 I/O pads;

a substrate with an adhesive (adsubstrate), and having

9 openings corresponding to the locations of said I/O pads;

and

12 ball mountings formed over said adsubstrate and reaching  
said UBM layer over said I/O pads on said chip.

2. The CSP of claim 1, wherein said first layer of I/O pads  
comprise aluminum alloy or copper.

3  
SUB A5 > 3. The method of claim 1, wherein said UBM layer comprises  
nickel or copper.

3  
4. The CSP of claim 1, wherein said substrate comprises  
bismaleimide triazine (BT).

3

5. The CSP of claim 1, wherein said substrate comprises Ball Grid Array (BGA).

3

6. The CSP of claim 1, wherein said substrate has a thickness <sup>A</sup> between about 150 to 300  $\mu\text{m}$ , and wherein said adhesive has a thickness between about 10 to 100  $\mu\text{m}$ .

3

7. The CSP of claim 1, wherein said ball mountings comprise tin-lead or tin-silver alloy.

3

8. The CSP of claim 1, wherein said ball mountings have a height between about 300 to 800  $\mu\text{m}$ .

3

9. The CSP of claim 1, wherein said I/O pads are area array (AA) type, or redistributed to a redistribution layer to form AA pads.

3

10. The CSP of claim 1, wherein said CSP is encapsulated in a molding material comprising epoxy resin.

3

11. A method of forming a chip scale package (CSP) comprising the steps of:

3

SUB  
A6

SUB 7  
A6

providing one or more chips having I/O pads with UBM layer on the surface of said I/O pads;

providing a substrate;

9 applying an adhesive layer over said substrate, thus forming an adsubstrate composite;

12 forming openings in said adsubstrate composite to match the spacing of corresponding said I/O pads of said chip;

15 attaching said chip(s) on said adsubstrate composite wherein said I/O pads of said chip(s) are placed on the corresponding openings on said adsubstrate composite to form

18 a package;

forming a molding material around said package;

21

performing ball mounting over said openings on said adsubstrate of said package; and

24

forming said CSP.

27

12. The method of claim 11, wherein said chip comprises silicon.

3

13. The method of claim 11, wherein said I/O pads are area array (AA) type, or are redistributed to a redistribution layer to form AA I/O pads.

3

14. The method of claim 11, wherein said substrate comprises bismaleimide triazine (BT).

3

15. The method of claim 11, wherein said substrate comprises Ball Grid Array (BGA).

3

16. The method of claim 11, wherein said substrate has a thickness between about 150 to 300  $\mu\text{m}$ .

3

17. The method of claim 11, wherein said adhesive layer comprises polyimide thermocompression adhesive.

3

18. The method of claim 11, wherein said adhesive layer has a thickness between about 10 to 100  $\mu\text{m}$ .

3

19. The method of claim 11, wherein said forming said openings is accomplished by mechanical or laser drilling, or screen printing.

3

3 20. The method of claim 11, wherein said openings have a diameter between about 350 to 900  $\mu\text{m}$ .

21. The method of claim 11, wherein said attaching said chip(s) is accomplished by subjecting said adsubstrate to a  
3 temperature between about 250 to 350  $^{\circ}\text{C}$  at a pressure between about 1.5 to 2.5 Mpascals.

22. The method of claim 11, wherein said molding material comprises epoxy resin.  
3

23. The method of claim 11, wherein said molding material has a thickness between about 100 to 500  $\mu\text{m}$ .  
3

24. The method of claim 11, wherein said performing said ball mounting is accomplished with a solder comprising tin-  
3 lead or tin-silver alloy.

25. The method of claim 11, wherein said ball mountings have a height between about 300 to 800  $\mu\text{m}$ .  
3

SUB  
A7  
26. A method of forming a chip scale package (CSP) comprising the steps of:  
3

SUB 7  
A7 6

providing a wafer having a plurality of chip sites with I/O pads;

forming an under-ball metal (UBM) layer over said I/O pads;

9 forming an adhesive layer over said UBM layer on said wafer to form an adwafer;

12 forming openings in said adhesive layer on said adwafer to reach said I/O pads underlying said UBM layer;

15 die sawing said adwafer to form said chip scale package (CSP);

18 providing a substrate having openings corresponding to said I/O pads;

21 attaching said CSP with said adhesive to said substrate; and

forming ball mountings on said openings on said substrate to

24 attach to said I/O pads on said CSP.

27. The method of claim 26, wherein said wafer comprises silicon.

28. The method of claim 26, wherein said I/O pads comprise aluminum alloy or copper.

3

29. The method of claim 26, wherein said I/O pads are area array (AA) type, or redistributed to a redistribution layer to form AA pads.

3

30. The method of claim 26, wherein said UBM layer comprises nickel and/or copper.

3

31. The method of claim 26, wherein said forming said adhesive layer over said UBM layer comprises lamination, spin coating or screen printing.

3

32. The method of claim 26, wherein said adhesive layer comprises thermocompression polyimide adhesive.

3

33. The method of claim 26, wherein said adhesive layer has a thickness between about 10 to 100  $\mu\text{m}$ .

3

34. The method of claim 26, wherein said forming said openings comprise laser drilling, photolithography, or silk screening.

3

35. The method of claim 26, wherein said openings have a diameter between about 250 to 750  $\mu\text{m}$ .

3

36. The method of claim 26, wherein said substrate comprises bismaleimide triazine (BT) having a thickness between about 150 to 300  $\mu\text{m}$ .

3

37. The method of claim 26, wherein said substrate comprises Ball Grid Array (BGA).

3

38. The method of claim 26, wherein said attaching said BGA substrate to said adhesive layer is accomplished at a temperature between about 250 to 350  $^{\circ}\text{C}$ , and pressure between about 1.5 to 2.5 Mpascals.

3

39. The method of claim 26, wherein said ball mountings comprise solder having a composition lead-tin or tin-silver.

3

40. The method of claim 26, wherein said mounting balls have a height between about 300 to 800  $\mu\text{m}$ .

3

41. The method of claim 26, wherein said CSP is encapsulated in a molding material comprising epoxy resin.